

# Leepoxy Plastics, Inc.

3706 W. Ferguson Rd., Fort Wayne, IN 46809  
Phone (260) 747-7411 Fax: (260) 747-7413

## TECHNICAL BULLETIN LEECURE B-115

### Description

LEECURE B-115 a moderately reactive member of Leepoxy's proprietary liquid BF<sub>3</sub> epoxy curing agent family. When mixed with standard epoxy Bisphenol A resin, LEECURE B-115 provides a rapid cure at modest temperatures, assuming little or no heat sink effect. LEECURE B-115's balance of pot life and reactivity makes it practical to dispense via meter-mix equipment or dual cartridge guns while maintaining high production throughput.

For higher performance applications, LEECURE B-115 can be used with epoxy novolac, and flexibilized epoxy resins. Cured systems offer exceptional chemical and heat resistance, tensile strength and electrical properties.

TYPICAL PROPERTIES	
Appearance	Brown liquid
Viscosity @ 25°C, cps	10,000
Density, pounds/gallon	9.3
Shelf life, months	12

### Handling and Mixing

Keep LEECURE B-115 containers tightly sealed at all times. Use of dry nitrogen is recommended to protect partial containers from moisture contamination. The epoxy resin, fillers,

and any other ingredients to be mixed should be moisture-free as well. Avoid alkaline fillers such as calcium carbonate. Fillers such as silica, barytes, glass, graphite, clays, and others that have a pH of 7 or lower are recommended. Mix very thoroughly in a dry mix vessel. No special equipment is necessary, but entrapment of excessive air bubbles should be avoided. Exposure to humidity in the air should be minimized from the time of mix until the product is ultimately heat cured because prolonged exposure to humidity may harm the reactivity, physical properties, and surface appearance of a LEECURE B-115 cured system.

TYPICAL HANDLING PROPERTIES	
Mix Ratio <sup>1</sup> , phr	8 – 12
Gel time @ 50°C, 10 g, minutes	21
@ 65°C, 10 g, minutes	6.5
@ 80°C, 10 g, minutes	3
Work Life @ 25°C, hours	4.5
Cure Time @ 65°C, 3/16 inch bead,	
Green Strength, minutes	6 – 10
Full Cure, minutes	10

<sup>1</sup> Mix ratio with Bisphenol A Resin (EEW=189)

### Curing Conditions

Epoxy compounds containing LEECURE B-115 should be cured so as to control the effects of the exothermic

reaction. The optimum time and temperature will depend on the particular formulation and the mass of compound. Longer cure schedules may be needed when curing thin sections or where the epoxy is adjacent to a mass of material that will act as a heat sink. The recommended minimum bondline cure temperature is 65°C. Generally, the higher the cure temperature, the better the heat resistance and physical properties of the cured systems.

Additives, modifiers, and diluents used in formulating epoxy compounds incorporating LEECURE B-115 may have a marked effect not only on the cure rate but also the final properties of the cured system. Diluents, fillers, and flexibilizers will generally increase pot life, gel time, and cure time.

<b>TYPICAL PERFORMANCE</b>	
Tensile Strength, psi	10,600
Tensile Modulus, psi	480,000
Tensile Elongation, %	4.0
Hardness, Shore D	90
Dielectric Constant, 1 mHz @ 25°C	3.9
Dissipation Factor, 1 mHz @ 25°C	0.018
Heat Deflection Temperature, °C	86

The Information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material. Freedom to use any patent owned by Leepoxy Plastics, Inc. or others is not to be inferred from any statement contained herein